


Sample #	Au g/t	Ag g/t	Pb ppm	Zn ppm
K434479	1.69	2.1	464	211
K434480	1.65	1.4	15	31
K434482	16.9	93.6	25300	1025
K434484	30	128	60600	748
K434485	10.45	17.2	1790	805
K434486	20.1	85.1	16800	3850
K434489	39.7	77.3	8880	10800
K434490	13.35	109	46900	559
K434491	2.06	1.5	366	292
K434492	3.33	11.9	3460	416
K434493	7.19	14.4	1235	129
K434494	4.38	19.6	9530	45



- FIGURE 1 (P-R 2018-09)**
- ★ Grab samples results 2018 > 1 g/t
 - Grab Samples 2018
- Mineralized quartz veins**
- Greek Vein
 - Line 4W
 - Baker Vein
 - Mersereau NE Ext. Vein
 - Mersereau Vein
 - Marleau Vein



NAME	LABEL
Greek Vein	Average grade at 0.65 g/t Au on exposed length of 10.67 m and with a average sample width of 0.252 m
Line 4W	Average grade at 1.47 g/t Au on exposed length of 42.99 m and with a average sample width of 0.46 m
Mersereau Vein	Average grade at 10.35 g/t Au, 133.03 g/t Ag, 5.52% Pb and 0.25% Zn on exposed length of 49.70 m and with a average sample width of 0.53 m
Baker Vein	Average grade at 13.54 g/t Au, 453.94 g/t Ag, 13.87% Pb and 0.43% Zn on exposed length of 41.46 m and with a average sample width of 0.72 m
Mersereau NE Ext. Vein	Average grade at 22.83 g/t Au, 80.23 g/t Ag, 3.68% Pb and 0.08% Zn on exposed length of 6.4 m and with a average sample width of 0.09 m
Marleau Vein	Average grade at 5.59 g/t Au on exposed length of 75.61 m and with a average sample width of 0.49 m

Drawing by : B.O Martel, Géo #492
Date : 2018-09-12
Project: Lac Arsenault
Coordinate System: NAD 1983 UTM Zone 20N
Projection: Transverse Mercator
Datum: North American 1983